"I SAW THE ANGEL IN THE MARBLE AND CARVED UNTIL I SET HIM FREE." - MICHELANGELO

HYATT'S All Things Creative" MOIST CLAY SELECTOR

BUFFALO & CLARENCE & ROCHESTER & EDINBORO & E-STORE: WWW.HYATTS.COM & PHONE: 716-884-8900 & FAX: 716-884-3943 & TOLL FREE: 800-23-HYATTS

AMADOR

An outstanding, all-purpose, orange/brown, moist body. Has fine sand and is a difficult body to crack during firing. Durable and affordable. Good for professional or student. Reduces a warm orange/brown, lighter in oxidation. 25lb. bag: x41500, 50lb. bag: x41510

SOLDATE 60

Gray in the raw form with a high sand content which makes it an ideal choice for large thrown pieces and sculptural forms. Fires to a yellow-brown color under medium reduction. It has a medium coarse texture due to 60 mesh sand additive. 50lb. bag: x41518

B-MIX

A premier, cream-white, throwing clay that is easy to throw and form. Excellent glaze results. Fires gray/white in reduction and lighter in oxidation. Smooth porcelain texture. 50lb. bag: x41512

HALF & HALF

This clay combines white stoneware and porcelain in equal proportions. The result is a very throwable white body that is tinted a light gray/white in reduction and slightly off-white in oxidation. Made with fine sand. 25lb. bag: x41501

DAVE'S PORCELAIN

An outstanding throwing body. Ideal for thin walls and larger pieces, and excellent for slab use and when a vitreous clay is desirable. Light gray in reduction, off-white in oxidation. 50lb. bag: x41514

DANISH WHITE

This white stoneware body is a good choice for small to medium work. It has exceptional strength and plasticity. Danish White fires offwhite in oxidation and grayish in reduction. It has a smooth texture. 50lb. bag: x41516

BUFF WITH SAND

The addition of sand to 52 Buff increases its strength and workability, making it a better choice for medium sized pieces. The texture is medium coarse. Cone 5 firing results in a buff color in oxidation and yellow/brown in reduction. 50lb. bag: x41520

| HYATT'S | | APPROX. | WET | FIRED COLOR | | | PENT. | AVG. | AVG. |
|-----------|------------------|---------|----------|-----------------|--------------|---------|--------------------|---------------|------------------|
| SKU | CLAY | CONE | COLOR | OXIDATION | REDUCTION | TEXTURE | PENT. TARGET ±0.5% | SHRINKAGE ±2% | WATER ABSOR. ±2% |
| X41500/10 | AMADOR | 10 | ORANGE | LT.ORANGE/BROWN | ORANGE/BROWN | SC | 7 | 12.00% | 1.30% |
| X41512 | B-MIX | 10 | CRM/WH | OFF-WHITE | GRAY/WHITE | S | 7 | 13.00% | 1.20% |
| X41501 | HALF AND HALF | 10 | GRAY | OFF-WHITE | GRAY/WHITE | SC | 7 | 12.00% | 1.70% |
| X41514 | DAVE'S PORCELAIN | 10 | WHITE | OFF-WHITE | LT.GRAY | S | 7 | 13.00% | 0.50% |
| X41516 | DANISH WHITE | 10 | lt. gray | OFF-WHITE | GRAY-WHITE | S | 7 | 12.00% | 0.80% |
| X41518 | SOLDATE 60 SAND | 10 | lt. gray | YELLOW/BUFF | YELLOW/BROWN | MC | 7 | 13.50% | 1.75% |
| X41520 | 52 BUFF w/SAND | 5 | BUFF | BUFF | YELLOW/BROWN | SC | 6.75 | 9.00% | 3.50% |

Legend: Texture: S:Smooth, SC: Slightly Coarse, MC:Medium Coarse, C:Coarse Pent.=Pentrometer Target or Moistness/Firmness